

WIPING STAIN 105

Description: 105 Wiping Stain Used on any unfinished wood surface, **105** is a little to no grain raising acrylic stain base developed to work with all of our series of sealers and finishes. Compatible with pigments and dyes for an unlimited range of colors. Offered in 18 standard stock colors of dye (best available clarity and warm colors), and pigment (good for evening out unmatched woods) with custom colors matched upon request. Designed for use when more open time and workability is needed in wiping applications. **105** may be spray applied then wiped from the surface, brushed or simply wiped on. Typical dry time to seal in ambient conditions is 30-45 minutes depending on substrate preparation and amount of stain applied. Product may be force dried with heat and air if proper flash time is allowed.

PRODUCT DATA & SPECIFICATIONS

Appearance & Odor:	Clear liquid, mild odor	VOC content by #:	0.248 #/gallon *
Evaporation Rate:	Slower than ether	VOC content by G/l:	30 Grams / liter *
Solubility in Water:	Dilutable	VHAP content:	0 *
Specific Gravity:	< 1.00	# VOC/gal solids:	1.77 *
Weight per Gallon:	8.35 #	Flash Point:	Non-combustible
Solids by Weight:	14 %	Flammability:	Not applicable
Solids by Volume:	14 %	Viscosity:	# 2 Zahn Cup, 20-30 seconds

Substrate Preparation: Substrate should be pre-sanded with 150 grit abrasive or higher. 220 grit abrasive is recommended for best results. Clean surface of all dust with lint free cloth.

Application: May be applied by spray, brush or wiping. Allow 45 minutes in ambient conditions for drying prior to sealer application.

Cleanup: Flush all equipment with water both before and after use of 105. Build-up may be removed with a cleaner solution such as 330 Universal Cleaner & Stripper. Flushing with water is necessary after the use of any cleaning agent to avoid contamination.

*VOC Amount calculation is based on the clear base. Tinted stain requires the use of Zero VOC Pigments and/or Dyes to meet these calculation amounts.

WOOD STAINS