

# SPRAY STAIN 155

**Description:** **155 Universal Stain** is a solvent free, interior water based stain designed for wood color enhancement before sealing and finishing. For use on any unfinished wood surface, **155** exhibits little to no grain raising and works in conjunction with all of the Fuhr series of sealers and finishes. Compatible with pigments and dyes for an unlimited range of colors. **155** is offered in 18 standard stock dye colors and 23 standard stock pigment colors. Designed as a fast dry spray stain, **155** imparts characteristics of traditional lacquer and alcohol spray stains. Spray no wipe, dip and wipe, shading, vacuum coating, and roll coating are all excellent application methods for **155** Universal Stain. Typical dry time to seal in ambient conditions is 15 minutes and dry times can be drastically reduced with the use of heat and air movement.

## PRODUCT DATA & SPECIFICATIONS

<b>Appearance &amp; Odor:</b>	Clear liquid, mild odor	<b>VOC content by #:</b> 0.0 #/gallon *
<b>Evaporation Rate:</b>	Slower than ether	<b>VOC content by G/l:</b> 0 Grams / liter *
<b>Solubility in Water:</b>	Dilutable	<b>VHAP content:</b> 0 *
<b>Specific Gravity:</b>	< 1.00	<b># VOC/gal solids:</b> 0 *
<b>Weight per Gallon:</b>	8.34 #	<b>Flash Point:</b> Non-combustible
<b>Solids by Weight:</b>	14 %	<b>Flammability:</b> Not applicable
<b>Solids by Volume:</b>	14 %	<b>Viscosity:</b> # 2 Zahn Cup, 20-30 seconds
<b>Coverage Rate:</b>	300-450 square ft.	

**Substrate Preparation:** Substrate should be pre-sanded with 150-220 grit aluminum oxide sandpaper is recommended for best results. Clean surface of all dust with lint free cloth or non-treated tack cloth.

**Application:** May be applied by spray, dipping, roll coating, or vacuum coating. Allow 15 minutes in ambient conditions for drying prior to sealer application.

**Cleanup:** Flush all equipment with water both before and after use of 155. Build-up may be removed with a cleaner solution such as 330 Universal Cleaner & Stripper. Flushing with water is necessary after the use of any cleaning agent to avoid contamination.

\*VOC Amount calculation is based on the clear base. Tinted stain requires the use of Zero VOC Pigments and/or Dyes to meet these calculation amounts.

WOOD STAINS